

PREMLYCRA KOM

LYCRA PREVENT AGENT

TECHNICAL GUIDE



TECHNICAL PROPERTIES

CHEMICAL STRUCTURE : Elastomers and fatty acid amids mixture.

APPERANCE : Ivory liquid

pH : 4.5 ± 6.5

SOLUBILITY : Complatly soluble in water

APPLICATIONS

PREMLYCRA KOM can be used to prevent the lycra fabric destroyed to be. Also the garments that lycra destroyed can be repair by PREMLYCRA KOM.

PREMLYCRA KOM may be applied as a single finishing agent or in the presenceof nonionic or cotionic softening agents and crease resist resins.

Apply in the final rinse bath at 30 - 35 °C for 15 - 20 minutes pH 4.5 - 5.5 a level of 0.5 - 5.0 % is recommended it may also be applied with nonionic or cationic softening agent.

If you dried high temperature (150 °C)obtain more elastic.

PACKAGING : 60 - 120 Kg package

STORAGE : It is recommended that to keep original drums and room temperature. Store for 6 months.

PREMLYCRA

Operating conditions and methods of application are beyond our control and are not legally binding guarantee that any product descriptions and application information contained in our catalog,not regarded as a kind of general wet process problems can call the technical service for the indigo

İNDİGO KİMYA VE TEKSTİL SANAYİ TİCARET LİMİTED ŞİRKETİ
S.S. ÇEVRE KÜÇÜK SANAYİ SİTESİ 6.BLOK NO:1-2-3 34306 İKİTELLİ-BAŞAKŞEHİR/İSTANBUL
TELEFON:0212 486 07 07 PBX FAX:0212 486 30 22

www.indigokimya.com.tr